

AMENDMENT NO. 2 MARCH 2017
TO
IS 4270 : 2001 STEEL TUBES USED FOR WATER
WELLS — SPECIFICATION

(Third Revision)

(Page 5, clause 8, first para) — Substitute the following for the existing para:

‘Hydrostatic test shall be carried out at a pressure as calculated by the following formula. Unless otherwise agreed, the hydraulic pressure shall not exceed 7 MPa. The holding time at test pressure shall not be less than 3 s and the pipe shall not show any leakage.’